SPARKLE

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	120 microns	Adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 19.HIT.86733 HOHENSTEIN HTTI VEGANOK AZIENDA N. 1004

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	45°	120 gf	20 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	hot

- → Mirror cut the design
- → Weed excess material
- → Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier hot

PRODUCT HIGHLIGHTS

- → Glittery finish
- → Smooth surface

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside-out	YES (synthetic cycle)	YES	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com
For further information, please contact our sales office: info@siser.it

Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246

TÜVRheinland CERTIFIED
Management System ISO 9001:2015 ISO 14001:2015
www.tuv.com ID 9105027958